

CLAIMS

1. A crosslinkable elastomer composition for plasma process comprising a crosslinkable elastomer and a carbon fluoride filler.

5

2. The crosslinkable elastomer composition of Claim 1, which further comprises a silicic compound inorganic filler and/or a filler comprising a synthetic polymer having a thermally and chemically stable aromatic ring in the main chain.

10

3. The crosslinkable elastomer composition of Claim 2, wherein said synthetic polymer having a thermally and chemically stable aromatic ring in the main chain is a synthetic polymer having an amide bond or an imide bond in the main chain.

15

4. The crosslinkable elastomer composition of Claim 2, wherein said silicic compound inorganic filler has average particle size of at most 0.5 μm .

20

5. The crosslinkable elastomer composition of Claim 2, wherein said filler comprising a synthetic polymer having a thermally and chemically stable aromatic ring in the main chain has specific surface area of at least 0.5 m^2/g .

25

6. The crosslinkable elastomer composition of Claim 1, 2, 3, 4 or 5, wherein said carbon fluoride filler is heat treated at 300 to 550°C in advance.

7. The crosslinkable elastomer composition of Claim 1, 2, 3, 4, 5 or 6, wherein said crosslinkable elastomer is a perfluoro elastomer.

8. A molded article for plasma process comprising the
5 crosslinkable elastomer composition of Claim 1, 2, 3, 4, 5, 6 or 7.

9. A sealing material for plasma process comprising the crosslinkable elastomer composition of Claim 1, 2, 3, 4, 5, 6 or 7.